

No. : GZIN1407018144MR Date : Jul 21, 2014 Page: 1 of 4

CUSTOMER NAME:	JIANGXI SHENG HUI OPTICAL TECHNOLOGY LIMITED COMPANY
ADDRESS:	CHUNQI RD ECONOMIC DEVELOPMENT ZONE YICHUN CITY
	JIANGXI

The following sample(s) was/ were submitted and identified on behalf of the client as:

Sample Name	:	DIFFUSION SHEET
SGS Ref. No.	:	XMML140703177
Product Specification	:	0.8MM
Manufacturer	:	JIANGXI SHENG HUI OPTICAL TECHNOLOGY LIMITED COMPANY
Material and Mark	:	PC
Date of Receipt	:	Jul 10, 2014
Testing Start Date	:	Jul 10, 2014
Testing End Date	:	Jul 21, 2014
Test result(s)	:	For further details, please refer to the following page(s)

Signed for SGS-CSTC Standards Technical Services Co., Ltd. GZ Branch Testing Center

Kelly Lee Authorized signatory

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <a href="http://www.sgs.com/en/Terms-and-Conditions/Terms-

-CSY Standards Technical Services 20, Ltd. 198 Keztu Road, Scientech Park Guargebou Economic & Technology Development District, Guargebou, China 510663 t (86-20) 82155555 f (86-20) 82075188 www.sgsgroup.com.cn ptm Brah 全观kges Jagain Londony Development District, Guargebou Economic & Technology Development District, Guargebou China 510663 t (86-20) 82155555 f (86-20) 82075188 e sgs.cchina@sgs.com



No. : GZIN1407018144MR

Date : Jul 21, 2014

Page: 2 of 4

Summary of Results:

No.	Test Item	Test Method	Result	Conclusion
1	Vertical Burning	UL 94-2013 Section 8	V-2	/

Note: Pass : Meet the requirements;


v Laboratory.

Gia

Fail : Does not meet the requirements;

/: Not Apply to the judgment.

Original Sample Photo:



This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <a href="http://www.sgs.com/en/Terms-and-Conditions/Terms-

is Technical Services 200.Ltd. 198 Kezhu Road, Scientech Park Guangzhou Economic & Technology Development Dishid, Guangzhou, China 510663 t (86–20) 82155555 f (86–20) 82075188 www.sgsgroup.com.cn

中国・广州・经济技术开发区科学城科珠路198号 邮编:510663 t(86-20)82155555 f(86-20)82075188 e sgs.china@sgs.com



No. : GZIN1407018144MR Date: Jul 21, 2014 Page: 3 of 4

Test Item: Vertical Burning

Sample Description: Plastic bar

Test Method: UL 94-2013 Section 8

Test Condition:

Specimen: 126 mm × 12.7 mm × 0.79 mm

Test Result:

Conditioning	23±2℃, 50±5%RH, 48h			70±2℃, 168h→ Desiccator, 23±2℃, 4h						
Specimen		2	3	4	5	1	2	3	4	5
Afterflame time after first flame application (s), t ₁		2.7	2.6	3.7	3.3	12.7	3.7	8.7	1.2	9.6
Afterflame time after second flame application (s), t ₂		4.8	9.4	4.6	8.2	4.6	4.8	6.2	12.7	5.1
Afterglow time after second application (s),t ₃		0	0	0	0	0	0	0	0	0
Total afterflame time for any condition set (s), t ₁ +t ₂	47.5		69.3							
Afterflame time plus afterglow time after second flame application (s), t_2+t_3	6.4	4.8	9.4	4.6	8.2	4.6	4.8	6.2	12.7	5.1
Whether or not specimens progressed up to the holding clamp		No	No	No	No	No	No	No	No	No
Whether or not specimens drip flaming particles and whether the particles ignited the cotton indicator		Yes	Yes	Yes	Yes	Yes	Yes	Yes	Yes	Yes

Classification: V-2 (See table 1)

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <a href="http://www.sgs.com/en/Terms-and-Conditions/Terms-

rds Technical Services P. 6, Ltd. | 198 Kezhu Road, Scientech Park Guangzhou Economic & Technology Development District, Guangzhou, China 510663 t (86–20) 82155555 f (86–20) 82075188 www.sgsgroup.com.cn

yLaboratory. 中国・广州・经济技术开发区科学城科珠路198号 邮编:510663 t(86-20) 82155555 f(86-20) 82075188 e sgs.china@sgs.com



No. : GZIN1407018144MR Date : Jul 21, 2014 Page: 4 of 4

Table 1

Criteria conditions	V-0	V-1	V-2
Afterflame time for each individual specimen $t_1 \text{ or } t_2$	≪10s	≪30s	≪30s
Total afterflame time for any condition set (t ₁ +t ₂ for 5 specimens)	≪50s	≪250s	≪250s
Afterflame plus afterglow time for each individual specimen after the second flame application (t ₂ +t ₃)	≪30s	≪60s	≪60s
Afterflame or afterglow of any specimen progress up to the holding clamp	No	No	No
Cotton indicator ignited by flaming particles or drops	No	No	Yes

******** End of report*******

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Termsand-Conditions.aspx and for electronic format documents, subject to Terms and Conditions for Electronic Documents at <a href="http://www.sgs.com/en/Terms-end-Conditions/Terms-e

SGS-CS1 Vandards Technical Services (0.1.Ld.) 198 Kezhu Road, Scientech Park Gangzhou Economical Technology Development District, Guargzhou, China 510663 t (96-20) 82155555 f (86-20) 82075188 www.sgsgroup.com.cn Gangzhou Bark - 200 Gangzhou Economical Technology Development District, Guargzhou, China 510663 t (96-20) 82155555 f (86-20) 82075188 e sgs.china@sgs.com