

Test Report

Number: GZHH00589470


Applicant: WECARE FURNITURE (LONGYAN) CO., LTD
NO.105, PEIFENG STREET NORTH ROAD,
PEIFENG TOWN, YONGDING DISTRICT,
LONGYAN CITY, FUJIAN CHINA

Date: Apr 10, 2025

Attn: DAVID TSANG

Sample Description:

Two (2) submitted samples said to be **MDF** used for :
Item Name : Gilleleje Daybed
Item No. : 3600496, 3600443
Manufacturer : Wecare Furniture (Longyan) Co.,Ltd
Color : White, Grey
Country of Destination : Europe
Country of Origin : China
Date Sample Received : Apr 01, 2025
Testing Period : Apr 01, 2025 to Apr 08, 2025



Tests conducted:

As requested by the applicant, refer to attached page(s) for details.

To be continued



Test Report

Number: GZHH00589470

Conclusion:

<u>Tested sample</u>	<u>Test Item</u>	<u>Result</u>
Submitted samples	Colour Fastness to Light - EN 15187: 2006 Furniture- Assessment of the effect of light exposure and client's requirement	Pass

Authorized by:
For Intertek Testing Services Shenzhen Ltd.
Guangzhou Branch, Hardlines



Victor T.J. Wang
General Manager



Should you have any query on this report, please click the link below:
https://verifyindex.intertek.com.cn/home/index?id=hl_report_verify



Test Report

Number: GZHH00589470

Tests Conducted

1 Colour Fastness to Light

As per EN 15187: 2024 Furniture- Assessment of the effect of light exposure and client's requirement, the tested sample was subjected to the following test.

Operating conditions:

- (1) Source = Xenon arc lamp.
- (2) Irradiance = EN 15187: 2024 Table 1.
- (3) Control Irradiance = 1.10W/m² at 420 nm.
- (4) Test atmosphere = Black standard temperature (BST): (55±3) °C; Chamber temperature: (38±3) °C; RH: (50±10) %

Exposure period = Blue wool standard No.6

Equipment: Xenon lamp aging tester

Assessment method:

Color change was assessed with reference to ISO 105-A02:1993 (grey scale).

Test result:

Tested sample	Test rating Grey scale	Client's requirement	Test result
Grey wood board	4-5	≥ Blue wool standard No.6	Pass
White wood board	4-5	≥ Blue wool standard No.6	Pass

Note: The grey scale was determined under the D65 standard light, the grade 5 is the best and the grade 1 is the worst.




Test Report

Number: GZHH00589470

Tests Conducted

Photos for reference



End of report

The statements of conformity reported have considered the decision rule agreed, namely that Intertek have taken account of measurement uncertainty as calculated by Intertek, and applied according to ILAC-G8/09:2019 (Non-binary acceptance based on guard band $w = U$) except designation from the customer, regulation or test specification. This decision rule only applies to the numeric test results.

The sample(s) and sample information hereto are provided by the client who shall be solely responsible for the authenticity and integrity thereof. The results shown in this report relate only to the sample(s) tested. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct. This report shall not be reproduced unless with prior written approval from Intertek Testing Services Shenzhen Limited, Guangzhou Branch.

